

Leona™ 1300S

Asahi Kasei Corporation - Polyamide 66

Tuesday, October 10, 2017

	Oeneral III			
General				
Material Status	 Commercial: Active 			
Availability	 Africa & Middle East 	• Europe		
Availability	 Asia Pacific 	 North America 		
Features	 Good Flow 	 Good Stiffness 	 Good Toughness 	
Uses	 Automotive Applications 	 Consumer Applications 		
	Connectors	 Fittings 		
	ASTM & ISO	Properties 1		
Physical	Dry	Conditioned	Unit	Test Method
Density / Specific Gravity	1.14		g/cm³	ASTM D792 ISO 1183
Molding Shrinkage - Flow	1.3 to 2.0		%	Internal Method
Water Absorption				
Saturation, 23°C		2.5	%	
Equilibrium, 23°C, 50% RH		2.5	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	3000	1200	MPa	ISO 527-2
Tensile Stress				
Yield, 23°C	82.0	52.0	MPa	ISO 527-2
	79.0	57.0	MPa	ASTM D638
Tensile Strain				
Yield, 23°C	4.0	24	%	ISO 527-2
Break	50	250	%	ASTM D638
Break, 23°C		> 100	%	ISO 527-2
Flexural Modulus				
	2800	1200	MPa	ASTM D790
23°C	2700	1100	MPa	ISO 178
Flexural Strength				
	118	54.0	MPa	ASTM D790
23°C	113	42.0	MPa	ISO 178
Taber Abrasion Resistance				ASTM D1044
1000 Cycles		7.00	mg	
mpact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength	6.0	15	kJ/m²	ISO 179
Charpy Unnotched Impact Strength	No Break	No Break		ISO 179
Notched Izod Impact	39	150	J/m	ASTM D256

General Information

Disclaimer:

Hardness

Rockwell Hardness

M-Scale

R-Scale

- Data shown are typical values obtained by proper testing methods and shoud not be used for specification purpose.
- Please use these data for selecting the most appropriate grade suitable for specific usage.
- These data may be changed because of improvement in properties.
- Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.
 Do not use plastics in any of the following orally-or medically-related applications.
- Orally-related application: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.
- For drinking water application, please consult Asahi Ksei Chemicals Corporation.
- Medically-related applications : any part,or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue , body fluids , or transfusion fluids.

Dry

80

120

Conditioned

55 108

J/m Unit

Test Method

ASTM D785 ISO 2039-2

Leona™ 1300S

Asahi Kasei Corporation - Polyamide 66

Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	230		°C	ASTM D648
0.45 MPa, Unannealed	190		°C	ISO 75-2/B
1.8 MPa, Unannealed	70.0		°C	ASTM D648 ISO 75-2/A
CLTE - Flow	8.0E-5		cm/cm/°C	ASTM D696
Specific Heat	1670		J/kg/°C	
Thermal Conductivity	0.20		W/m/K	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13		ohms	ASTM D257 IEC 60093
Volume Resistivity				
	1.0E+14		ohms·cm	ASTM D257
23°C	1.0E+14		ohms·cm	IEC 60093
Dielectric Strength	20		kV/mm	ASTM D149 IEC 60243-1
Comparative Tracking Index				IEC 60112
3.00 mm	600		V	
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.75 mm)	V-2			UL 94
Glow Wire Flammability Index				IEC 60695-2-12
3.0 mm	960		°C	
Oxygen Index	26		%	ASTM D2863

Notes

Disclaimer:

- Data shown are typical values obtained by proper testing methods and shoud not be used for specification purpose. Please use these data for selecting the most appropriate grade suitable for specific usage.
- These data may be changed because of improvement in properties.

 Be sure to read the relevant SDS before handling and use, and always follow the Important Precautions.

 Do not use plastics in any of the following orally-or medically-related applications.
- Orally-related application: any part, device or component which may come into direct oral contact or into direct contact with drinking foods or beverages.
- For drinking water application, please consult Asahi Ksei Chemicals Corporation.

 Medically-related applications: any part, or component which may be used intracorporeally or which may in dialysis or other processes come into direct or indirect contact with body tissue, body fluids, or transfusion fluids.

¹ Typical properties: these are not to be construed as specifications.