



Test Report No. F691524/LF-CTSAYAA16-65712

Issued Date: 2016. 01. 13 Page 1 of 3

To: KOREA ENGINEERING PLASTICS (ULSAN)
578-26
Maeam-dong
Nam-ku
Ulsan
Korea

The following sample(s) was/were submitted and identified by/on behalf of the client as :

SGS File No. : AYAA16-65712
Product Name : KEPITAL 5
Item No./Part No. : F25-03H
Received Date : 2016. 01. 07
Test Period : 2016. 01. 07 TO 2016. 01. 13

=====

Test Requested : As specified by client, selected parts of the submitted sample(s) for compliance with American Food and Drug Administration (FDA) 21 CFR 177.1350 (Condition of use E).

Test Result(s) : Please refer to next page(s).

Timothy Jeon
Jinhee Kim
Cindy Park
Jerry Jung/ Testing Person

SGS Korea Co. Ltd.

Jeff Jang / Chemical Lab Mgr

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 180 days only.



Test Report No. F691524/LF-CTSAYAA16-65712

Issued Date: 2016. 01. 13 Page 2 of 3

To: **KOREA ENGINEERING PLASTICS (ULSAN)**

578-26

Maeam-dong

Nam-ku

Ulsan

Korea

Test Result(s)

PART NAME No.1 : WHITE PLASTIC

PASS

Test Item (s)	Unit	Method	MDL	Result	Limit
				No.1	
Total nonvolatile extractives (D.I.-Water, 120°F, 24 hours)	mg/in ²	With reference to CFR Title 21, Pt 177.1350 condition E.	-	0.11	0.5
Total nonvolatile extractives (n-Heptane, 70°F, 30 min)	mg/in ²	With reference to CFR Title 21, Pt 177.1350 condition E.	-	0.14	0.5
Total nonvolatile extractives (8% Alcohol, 120°F, 24 hours)	mg/in ²	With reference to CFR Title 21, Pt 177.1350 condition E.	-	0.09	0.5
Total nonvolatile extractives (50% Alcohol, 120°F, 24 hours)	mg/in ²	With reference to CFR Title 21, Pt 177.1350 condition E.	-	0.27	0.5

Note :

- 0.1wt% = 1000ppm ; mg/kg = ppm
- MDL = Method Detection Limit
- " - " = Not Regulated
- This report supersedes the previous document bearing the test report number CY/2012/21575A which was issued on 2012/03/01.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 180 days only.



Test Report No. F691524/LF-CTSAYAA16-65712

Issued Date: 2016. 01. 13 Page 3 of 3

To: KOREA ENGINEERING PLASTICS (ULSAN)
578-26
Maeam-dong
Nam-ku
Ulsan
Korea

*** The tested sample / part is marked by an arrow if it's shown on the photo. ***

AYAA16-65712



**** End of Report ****

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 180 days only.